



modern karton



Modkraft

TİPİK DEĞERLER

TEST	Metot	Birim	MODKRAFT				
Gramaj	T 410	g/m ²	110	115	125	135	140
Rutubet	T 412	%	8,0	8,0	8,0	8,0	8,0
Patlama	T 403	kPa	293	295	311	351	357
Patlama indeksi	T 403	kPa m ² /g	2,66	2,61	2,46	2,60	2,51
SCT CD	T 826	kN/m	1,97	2,07	2,25	2,31	2,40
SCT CD indeksi	T 826	kN.m/g	17,9	18,0	18,0	17,1	17,1
Cobb60 üst	T 441	g/m ²	32	32	32	32	32

GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	MODKRAFT				
Gramaj	T 410	g/m ²	% ± 5,5	110	115	125	135	140
Rutubet	T 412	%	± 1,5	8,0	8,0	8,0	8,0	8,0
Patlama	T 403	kPa	min	275	288	300	324	336
Patlama indeksi	T 403	kPa m ² /g	min	2,5	2,5	2,4	2,4	2,4
SCT CD	T 826	kN/m	min	1,82	1,9	2,05	2,12	2,2
SCT CD indeksi	T 826	kN.m/g	min	16,5	16,5	16,4	15,7	15,7
Cobb60 üst	T 441	g/m ²	± 10	30	30	30	30	30

Test şartları

23±1°C, 50% ± 2% RH

ISO 9001:2015
ISO 14001:2015
OHSAS 18001:2007
ISO 50001:2011
TS 12728



Geçerlilik tarihi: Nisan 2018'den itibaren