



**modern karton**

**NSSC**



**TİPİK DEĞERLER**

TEST	Metot	Birim	NSSC			
Gramaj	T 410	g/m <sup>2</sup>	125	140	150	175
Rutubet	T 412	%	8,0	8,0	8,0	8,0
CMT index	T 809	Nm <sup>2</sup> /g	2,75	2,85	2,80	2,60
SCT CD	T 826	kN/m	2,25	2,60	2,92	3,04
SCT CD indeksi	T 826	kN.m/g	17,7	18,4	19,4	17,4
Cobb60 üst	T 441	g/m <sup>2</sup>	30	30	30	30
Cobb60 alt	T 441	g/m <sup>2</sup>	35	35	35	35

**GARANTİ EDİLEN DEĞERLER**

TEST	Metot	Birim	Tolerans	NSSC			
Gramaj	T 410	g/m <sup>2</sup>	% ± 4	125	140	150	175
Rutubet	T 412	%	± 1,5	8	8	8	8
CMT index	T 809	Nm <sup>2</sup> /g	min	2,4	2,4	2,4	2,4
SCT CD	T 826	kN/m	min	2,05	2,30	2,30	2,50
SCT CD indeksi	T 826	kN.m/g	min	16,4	16,4	15,3	14,3
Cobb60 üst	T 441	g/m <sup>2</sup>	± 15	30	30	30	30
Cobb60 alt	T 441	g/m <sup>2</sup>	± 15	30	30	30	30

Test şartları

23±1°C, 50% ± 2% RH

ISO 9001:2008  
ISO 14001:2004  
OHSAS 18001:2007  
ISO 50001:2011  
TS 12728



The mark of  
responsible forestry

Geçerlilik tarihi: Temmuz 2017'den itibaren

URN-ST-06 -Rev.2  
28.07.2017

SBL-20/Rev.00