



**modern karton**

# Testliner



## TİPİK DEĞERLER

| TEST            | Metot | Birim                 | TESTLINER |      |      |      |      |
|-----------------|-------|-----------------------|-----------|------|------|------|------|
| Gramaj          | T 410 | g/m <sup>2</sup>      | 90        | 100  | 115  | 125  | 140  |
| Rutubet         | T 412 | %                     | 8,2       | 8,2  | 8,2  | 8,2  | 8,2  |
| Cobb60          | T 441 | g/m <sup>2</sup>      | 35        | 35   | 35   | 35   | 35   |
| Patlama         | T 403 | kPa                   | 170       | 200  | 249  | 263  | 278  |
| Patlama indeksi | T 403 | kPa m <sup>2</sup> /g | 1,89      | 2,00 | 2,17 | 2,10 | 1,98 |

## GARANTİ EDİLEN DEĞERLER

| TEST            | Metot | Birim                 | Tolerans | TESTLINER |     |     |      |      |
|-----------------|-------|-----------------------|----------|-----------|-----|-----|------|------|
| Gramaj          | T 410 | g/m <sup>2</sup>      | % ± 5,5  | 90        | 100 | 115 | 125  | 140  |
| Rutubet         | T 412 | %                     | ± 1,5    | 8,5       | 8,5 | 8,0 | 8,0  | 8,0  |
| Cobb60          | T 441 | g/m <sup>2</sup>      | ± 15     | 35        | 35  | 35  | 35   | 35   |
| Patlama         | T 403 | kPa                   | min      | 153       | 170 | 219 | 219  | 245  |
| Patlama indeksi | T 403 | kPa m <sup>2</sup> /g | min      | 1,7       | 1,7 | 1,9 | 1,75 | 1,75 |

Test şartları

23±1°C, 50% ± 2% RH

ISO 9001:2008  
ISO 14001:2004  
OHSAS 18001:2007  
ISO 50001:2011  
TS 12728



The mark of  
responsible forestry

Geçerlilik tarihi: Temmuz 2017'den itibaren

URN-ST-02 -Rev.9  
15.11.2017

SBL-20/Rev.00