



**modern karton**

## Testliner3



### TİPİK DEĞERLER

TEST	Metot	Birim	TESTLINER3		
Gramaj	T 410	g/m <sup>2</sup>	90	100	115
Rutubet	T 412	%	8,2	8,1	8,0
Patlama	T 403	kPa	149	161	184
Patlama indeksi	T 403	kPa m <sup>2</sup> /g	1,65	1,61	1,60

### GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	TESTLINER3		
Gramaj	T 410	g/m <sup>2</sup>	% ± 5,5	90	100	115
Rutubet	T 412	%	± 1,5	8,5	8,5	8,0
Patlama	T 403	kPa	min	126	140	161
Patlama indeksi	T 403	kPa m <sup>2</sup> /g	min	1,4	1,4	1,4

Test şartları 23±1°C, 50% ± 2% RH

ISO 9001:2008  
ISO 14001:2004  
OHSAS 18001:2007  
ISO 50001:2011  
TS 12728



The mark of  
responsible forestry

Geçerlilik tarihi: Temmuz 2017'den itibaren