



**modern karton**

# Testliner



## TİPİK DEĞERLER

TEST	Metot	Birim	TESTLINER				
Gramaj	T 410	g/m <sup>2</sup>	90	100	115	125	140
Rutubet	T 412	%	8,2	8,2	8,2	8,2	8,2
Cobb60	T 441	g/m <sup>2</sup>	35	35	35	35	35
Patlama	T 403	kPa	170	200	249	263	278
Patlama indeksi	T 403	kPa m <sup>2</sup> /g	1,89	2,00	2,17	2,10	1,98

## GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	TESTLINER				
Gramaj	T 410	g/m <sup>2</sup>	% ± 5,5	90	100	115	125	140
Rutubet	T 412	%	± 1,5	8,5	8,5	8,0	8,0	8,0
Cobb60	T 441	g/m <sup>2</sup>	± 15	35	35	35	35	35
Patlama	T 403	kPa	min	153	170	219	219	245
Patlama indeksi	T 403	kPa m <sup>2</sup> /g	min	1,7	1,7	1,9	1,75	1,75

Test şartları

23±1°C, 50% ± 2% RH

ISO 9001:2015  
ISO 14001:2015  
OHSAS 18001:2007  
ISO 50001:2011  
TS 12728



Geçerlilik tarihi: Nisan 2018'den itibaren

URN-ST-02 -Rev.10  
24.05.2018

SBL-20/Rev.01