



Testliner

TİPİK DEĞERLER

TEST	Metot	Birim	TESTLINER				
Gramaj	T 410	g/m ²	90	100	115	125	140
Rutubet	T 412	%	8,2	8,2	8,2	8,2	8,2
Patlama	T 403	kPa	170	200	249	263	278
Patlama indeksi	T 403	kPa.m ² /g	1,89	2,00	2,17	2,10	1,98
Cobb60 üst	T 441	g/m ²	35	35	35	35	35

GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	TESTLINER				
Gramaj	T 410	g/m ²	% ± 4	90	100	115	125	140
Rutubet	T 412	%	± 1,5	8,5	8,5	8,0	8,0	8,0
Patlama	T 403	g/m ²	min	153	170	219	219	245
Patlama indeksi	T 403	kPa	min	1,70	1,70	1,90	1,75	1,75
Cobb60 üst	T 441	kPa.m ² /g	± 15	40	40	40	40	40

Test Şartları 23±1°C, 50% ± 2% RH

ISO 9001:2015
ISO 14001:2015
ISO 45001:2018
ISO 50001:2018
TS 12728



*Kuru, yağlı olmayan, soyulabilir, yıkanabilir gıdalar ile temasa uygundur.
İşletme Kayıt No:TR-59-K-016501

