



modern karton

Fluting



TİPİK DEĞERLER

TEST	Metot	Birim	FLUTING									
Gramaj	T 410	g/m ²	80	85	90	100	112	125	135	140	175	
Rutubet	T 412	%	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	8,0	
SCT CD	T 826	kN/m	1,19	1,32	1,40	1,57	1,77	1,88	2,03	2,06	2,54	
SCT CD indeksi	T 826	kN.m/g	14,9	15,5	15,6	15,7	15,8	15,0	15,0	14,7	14,5	

GARANTİ EDİLEN DEĞERLER

TEST	Metot	Birim	Tolerans	FLUTING									
Gramaj	T 410	g/m ²	% ± 5,5	80	85	90	100	112	125	135	140	175	
Rutubet	T 412	%	± 1,5	8,5	8,5	8,5	8,5	8,0	8,0	8,0	8,0	8,0	
SCT CD	T 826	kN/m	min	1,15	1,25	1,32	1,35	1,45	1,65	1,78	1,85	2,40	
SCT CD indeksi	T 826	kN.m/g	min	14,4	14,7	14,7	13,5	12,9	13,2	13,2	13,2	13,7	

Test şartları 23±1°C, 50% ± 2% RH

ISO 9001:2015
ISO 14001:2015
OHSAS 18001:2007
ISO 50001:2011
TS 12728



The mark of
responsible forestry

Geçerlilik tarihi: Nisan 2018'den itibaren